

**TECHNICAL SPECIFICATION 260
BITUMINOUS DRIVEWAY SEALER**

260.1 SCOPE OF WORK

This technical specification covers the furnishing of all labor, materials, tools, and equipment necessary to apply two coats of driveway sealer to all new bituminous driveway surfaces where the existing driveway was sealed or marked "Sealed" on the project plans, or as directed by the Engineer.

260.2 MATERIALS

The sealer shall be a coal tar emulsion meeting Federal Specification RP-355e.

260.3 CONSTRUCTION METHODS

Two coats of sealer shall be applied to all new bituminous driveway surfaces and shall extend one foot past the joint onto the existing pavement. Sealer shall not be applied to wet pavement nor when the temperature is less than 60°F or more than 90°F. The manufacturer's recommendation shall be followed with regards to the curing time of the pavement prior to the sealer being applied. Surfaces shall be thoroughly cleaned to the satisfaction of the Engineer. A minimum of six (6) hours shall elapse between the first and second coats.

260.4 MEASUREMENT

Measurement for this item will be based on the number of square yards sealed and accepted with two coats of driveway sealer.

260.5 PAYMENT

Payment for this item will be based on the contract unit price per Square Yard for two coats of driveway sealer completed, and accepted in place, including all labor, materials, tools, and equipment necessary to complete the work as specified.

PAY ITEM	PAY UNIT
Bituminous Driveway Sealer	S. Y.